



QUALITEK®

392-35 Liquid Flux, No-Clean for Lead Free applications.

DESCRIPTION

392-35 no-clean is a homogeneous mixture of halogen-free, low solids organic flux designed for wave-soldering conventional and surface mount PCB assemblies. 392-35 provides superior foaming characteristics with a uniform, stable head of small bubbles. 392-35 exhibits excellent wetting and fluxing activities with essentially no residue left on the assembly after soldering. 392-35 eliminates the expense of cleaning without surface insulation resistance degradation.

BENEFITS

- Bellcore compliant
- Excellent wetting
- Bright, shiny solder joints
- Low residue
- Rosin/Resin free
- Pin testable

APPLICATION METHODS

For mass wave soldering of bare copper and solder plated circuit boards. 392-35 flux can be applied by foam, spray, or wave methods. Flux deposition, density, and uniformity are critical to successful use of low solids no-clean flux. After foam or wave application, an air knife should be used to remove excess flux from the assembly. Pre-heating the assembly will partially volatilize the solvents, enhance oxide removal, and promote optimum wicking as well as superior solder joint formation. The degree of pre-heat is dependent on many variables; such as type of components, substrates, and conveyor speed. The optimum pre-heat temperature range is 90°-110°C on the top side of the circuit board and the optimum solder temperature should be 255-265C..

PACKAGING & STORAGE

392-35 flux is available in 5ltr, 20ltr and 200 ltr containers. It should be stored in cool, dry place away from ignition sources.

PHYSICAL & CHEMICAL CHARACTERISTICS

| | |
|--|---------------------------------|
| Color and Appearance | Light Straw Liquid |
| Solids Content, % (By Wt.) | 4.55 |
| Specific Gravity | 0.810 +/- 0.006 |
| Flash Point | 53°F |
| Surface Insulation Resistance -Ohms | |
| J-STD-004 | >1.00 x 10 ¹¹ |
| Acid Number | 40-45 |
| Flux Classification per J-STD-004 | ORL0 |
| Copper Mirror Test | Pass (No complete breakthrough) |
| Silver Chromate Test | |
| Chloride and Bromide | Pass (No discoloration) |
| Spot Test (Flouride) | Pass (No color change) |
| Corrosion Test | Pass (No evidence of corrosion) |
| Shelf life (un-opened) | 2 years |

PROCESS CONTROL

Control of the flux is necessary to ensure a consistent amount of flux is applied to assemblies. Due to the very low solids percentage of no-clean fluxes, specific gravity is not an accurate measure for solids content. Monitoring and controlling acid number is recommended to maintain the proper flux concentration. Titration may be accomplished with the Qualitek HDT-200 Digital Titration Kit. Control of the flux can be achieved with Qualitek 300A thinner. Debris and contaminants will accumulate in the flux reservoir. Periodically, the replacement of the flux is required for consistent soldering performance, and to prevent debris build-up on the circuit assembly. This should be performed every 35-40 hours of operation. Note:- If flux is applied by spraying application, flux control is not required and replacement of flux due to contamination also does not apply.

Qualitek® is a trademark of Qualitek International, Inc.

TEL: +44 (0) 151 334 0888 FAX: +44 (0) 151 346 1408 E-mail: sales@qualitek-europe.com Internet: www.qualitek.com
9 Apex Court, Bassendale Road, Wirral International Business Park, Bromborough, Wirral, CH62 3RE

QUALITEK

WORLDWIDE BRANCHES: UNITED KINGDOM – MEXICO – CHINA – PHILIPPINES – SINGAPORE-USA

This data is based on information that the manufacturer believed to be reliable and offered in good faith. Qualitek International, Inc. makes no warranties expressed or implied as to its accuracy and assumes no responsibilities and liabilities arising out of its use by others as conditions and methods of use of the products is beyond the control of Qualitek International, Inc. The user must determine the suitability of the product before using it on a commercial basis. The warranties extend only to the conformity of the product to the physical descriptions. In no event will Qualitek International, Inc. be responsible for special, incidental and consequential damages whether the claim is in contract, negligence or otherwise.