

Grove Sales Limited  
Unit 3 Beaver Industrial Estate  
8 Airfield Road  
Christchurch  
Dorset  
BH23 3TG

**Specification for Electrically Conductive Fibreboard**

T 01202 588900

F 01202 588901

E sales@grovesales.co.uk

W www.grovesales.co.uk

**Principle components:**

Cellulose fibre (from selected recycled paper)

Water

Dyestuffs, conductive materials

**Physical Characteristics:**

Thickness: 1.4 mm  $\pm$  0.1 mm

Moisture content: 6 – 11%

Specific gravity: 1.1 nominal

Board Colour: dark grey/black

Tensile strength: Machine direction ( kg/cm<sup>2</sup> minimum ) 350

Cross machine direction “ “ 175

Resistivity:  $1 \times 10^6$  Ohms –  $1 \times 10^5$  Ohms at 500 volts

Board is normally coated both sides with water based conductive paint for appearance purposes.

This message is intended solely for the person to whom it is addressed and may contain confidential or privileged information.  
If you have received it in error please notify us immediately and destroy this fax and any information enclosed with it.